


F40100 TRUST film Glossy 175

Microporous Coated Transparent Film

Printability

- simplex printable



Product Specification

Property	Test Method	Dimension	Target	Tolerance
Weight	DIN EN ISO 536	g/m ²	180	± 6
Thickness	DIN EN ISO 534	µm	138	± 8
	DIN EN ISO 536	mil	5.4	± 0.3
Gloss BYK	ISO 2813	60°	>100	

Printing Technology

- Inkjet water-based systems

Key Applications

- Positive or negative repro artwork for screen and pad printing
- Proof & Prepress

Benefits & Properties

- Instant dry
- High density range
- High ink absorption
- Good mechanical properties

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

felix-schoeller.com



FELIX SCHOELLER