
# H62110 ULTRA Glossy 240

# **Microporous Resin-Coated Paper**

# Printability

• simplex printable



#### **Product Specification**

Property	Test Method	Dimension	Target	Tolerance
Weight	DIN EN ISO 536	g/m²	236	± 7
Thickness	DIN EN ISO 534	μm	235	± 6
	DIN EN ISO 536	mil	9.3	± 0.23
Gloss BYK	ISO 2813	60°	45	± 5
Colour Elrepho UVO (D65)	ISO 2469	L	94,5	± 0,6
		а	-0,2	± 0,4
		b	-1,8	± 0,7
		delta b	9,9	± 0,7
CIE Whiteness (D65/10°) min.	ISO 2469		> 134	
Opacity min.	ISO 2469	%	> 90	

### **Printing Technology**

lnkjet water-based

#### **Key Applications**

- Photos
- Photo cards
- Photo cards
- Photo Retail
- $\cdot$  Poster / Wall Decoration



Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifcations reserved. In case of question, please contact the Felix Schoeller product management.

# H62110 ULTRA Glossy 240

### **Microporous Resin-Coated Paper**

#### **Benefits & Properties**

- Pin-sharp details
- High colour consistency and gamut
- Vivid colours
- High colour consistency
- $\cdot$  Water resistance
- High opacity
- High light fastness
- Outstanding lay-flat performance

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

FELIX SCHOELLER

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

#### felix-schoeller.com