

H62610 | ULTRA Pyramid 250

MICROPOROUS RESIN-COATED PAPER

PRODUCT SPECIFICATION *

| | | | |
|--|------------------|-------|-------|
| Weight DIN EN ISO 536 | g/m ² | 250 | ± 7 |
| Thickness DIN EN ISO 534 | µm | 255 | ± 6 |
| | mil | 10.0 | ± 0.2 |
| Gloss BYK (60°) ISO 2813 | | 8 | ± 5 |
| Colour Elrepho UVO (D65) ISO 2469 | L | 94,3 | ± 0,8 |
| | a | -0,2 | ± 0,5 |
| | b | -1,8 | ± 0,8 |
| | delta b | 9,8 | ± 0,8 |
| CIE whiteness (D65/10°) min. ISO 2469 | | > 136 | |
| Opacity min. ISO 2469 | % | > 90 | |

Printability

Simplex printable

Laminatability

Hot & cold

Printing Technology

💧 Inkjet water-based

Compatibility

Can be used on all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

BENEFITS & PROPERTIES

- Extraordinary hexagonal texture
- Unique look and feel
- Pin-sharp details
- Vivid colours
- High colour consistency and gamut
- High opacity
- High light fastness
- Water resistance
- Outstanding lay-flat performance
- Copy-protected

KEY APPLICATIONS

Wall Decoration

- Posters
- Large-format photo prints

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 02/2016