

# H6431 I | TRUST premium Satin I90

MICROPOROUS RESIN-COATED PAPER

## PRODUCT SPECIFICATION \*

<b>Weight</b> DIN EN ISO 536	g/m <sup>2</sup>	201	± 6
<b>Thickness</b> DIN EN ISO 534	µm	209	± 6
	mil	8.2	± 0.2
<b>Gloss BYK (60°)</b> ISO 2813		19	± 5
<b>Colour Elrepho UVO (D65)</b> ISO 2469	L	94,2	± 0,5
	a	-0,2	± 0,3
	b	-2,6	± 0,5
	delta b	<	0,7
<b>il Pro2</b>	L M0	95,3	
	a M0	-0,3	
	b M0	-2,7	
	L M1	95,3	
	a M1	-0,3	
	b M1	-3,0	
<b>CIE whiteness (D65/10°) min.</b> ISO 2469		> 94	
<b>Opacity min.</b> ISO 2469	%	> 93	

### Printability

Simplex printable

### Printing Technology

💧 Inkjet water-based

### Compatibility

Kompatibel auf allen handelsüblichen thermal und Piezo wasserbasierenden Drucksystemen wie Epson, Canon, Hewlett-Packard, Kodak, Encad etc. Dieses Papier hat die Bedingungen der FOGRA-Zertifizierung erfüllt!

### Certificates



Fogra 25488-5

## BENEFITS & PROPERTIES

- Reproducibility by outstanding media colour consistency
- Suitable for spot colours
- Large colour gamut
- No matting due to a high ink load
- Instant dry

## KEY APPLICATIONS

### Proof & Prepress

- Proofs for offset, gravure and screen printing
- Dot-proofs
- Contract, design and check proofs
- Mock-ups

### Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

\* Modifications reserved.

Version 01/2016