


H71610 TRUE photo Pyramid 275

Microporous Resin-Coated Paper

Printability

- simplex printable



Product Specification

Property	Test Method	Dimension	Target	Tolerance
Weight	DIN EN ISO 536	g/m ²	272	± 6
Thickness	DIN EN ISO 534	µm	275	± 6
	DIN EN ISO 536	mil	10.8	± 0.23
Gloss BYK	ISO 2813	60°	8	± 5
Colour Elrepho UVO (D65)	ISO 2469	L	94,3	± 0,8
		a	-0,2	± 0,5
		b	-1,8	± 0,8
		delta b	9,8	
CIE Whiteness (D65/10°) min.	ISO 2469		> 136	
Opacity min.	ISO 2469	%	> 90	

Printing Technology

- Inkjet water-based

Key Applications

- Exhibitions
- Fine Art
- Photos
- Photo prints
- Portfolio folders
- Professional Photo & Fine Art
- Professional photo albums

Version: 10/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

felix-schoeller.com



FELIX SCHOELLER

H71610 TRUE photo Pyramid 275

Microporous Resin-Coated Paper

Benefits & Properties

- Pin-sharp details
- High colour consistency and gamut
- Vivid colours
- High colour consistency
- Unique look and feel
- Extraordinary hexagonal texture
- Water resistance
- High opacity
- High light fastness
- Outstanding lay-flat performance
- Copy-protected

Version: 10/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

felix-schoeller.com



FELIX SCHOELLER