H90230 | SLP RC SATIN | 225

RESIN-COATED PAPER WITH SLP

PRODUCT SPECIFICATION *

Weight DIN EN ISO 536	g/m²	226	± 7
Thickness DIN EN ISO 534	μm mil	213 8.4	± 7 ± 0.27
Gloss BYK (60°) ISO 2813		22	± 5
Colour Elrepho UVO (D65) ISO 2469	L a b delta b	93.7 -0.3 -1.6 11.0	± 0.6 ± 0.4 ± 0.6 ± 0.6
CIE whiteness (D65/10°) min. ISO 2469		> 142	
Opacity min. ISO 2469	%	> 94	

Printability

Simplex printable

Laminatability

Hot & cold

Printing Technology

- ♦ Inkjet solvent
- ♦ Inkjet latex
- ♦ Inkjet UV

Compatibility

Excellent results on all eco, mild and hard solvent printers as well as on latex and UV printers.

BENEFITS AND PROPERTIES

- > Pin-sharp details
- > Vivid colours
- > High colour consistency and gamut
- Optimum handling properties
- > High light fastness
- Outdoor durability
- Outstanding lay-flat performance
- > Fast dry
- > PVC free

KEY APPLICATIONS

Sign & Display Graphics

- > POS signage
- > Exhibition graphics
- > Photo prints
- Commercial posters for indoor and outdoor applications

Directions for use

Store material only in original packaging under normal climatic conditions ($23^{\circ}C$, 50° RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 03/2021

