

J23160 | TRUE baryta Baryta 310

MICROPOROUS BARYTA-COATED PAPER

PRODUCT SPECIFICATION *

Weight DIN EN ISO 536	g/m ²	305	± 7
Thickness DIN EN ISO 534	µm	310	± 15
	mil	12.2	± 0.6
Gloss BYK (60°) ISO 2813		15	± 5
Colour Elrepho UVO (D65) ISO 2469	L	97,1	± 0,6
	a	-0,1	± 0,5
	b	1,1	± 1,0
	delta b	2,8	± 1,0
CIE whiteness (D65/10°) min. ISO 2469		> 98	
Opacity min. ISO 2469	%	> 95	

Printability

Simplex printable

Printing Technology

💧 Inkjet water-based

Compatibility

Can be used on all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

Certificates



Paper Aging (ISO 9706) | 29112

Fogra 29 | 12



DIN EN ISO 9706

BENEFITS & PROPERTIES

- Smell, look and feel of a traditional baryta photo paper
- Pin-sharp details
- High colour consistency and gamut
- Maximum optical densities (D_{max} of ≥ 2.4)
- Made from true baryta rawbase
- Acid free
- Lignin free
- Calcium carbonate buffered
- Excellent archivability

KEY APPLICATIONS

Professional Photo & Fine Art

- High-end photo prints
- Portfolio folders
- Exhibitions
- Black and white photography

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 02/2016