

P503 I I | TRUST premium Satin 200

MICROPOROUS RESIN-COATED PAPER

PRODUCT SPECIFICATION *

Weight DIN EN ISO 536	g/m ²	202	± 6
Thickness DIN EN ISO 534	µm	208	± 6
	mil	8.2	± 0.2
Gloss BYK (60°) ISO 2813		19	± 5
Colour Elrepho UVO (D65) ISO 2469	L	94,5	± 0,5
	a	0,5	± 0,3
	b	-1,6	± 0,5
	delta b	2,8	± 0,5
il Pro2	L M0	95,6	
	a M0	1,0	
	b M0	-4,0	
	L M1	95,6	
	a M1	1,2	
	b M1	-5,3	
CIE whiteness (D65/10°) min. ISO 2469		> 105	
Opacity min. ISO 2469	%	> 92	

Printability

Simplex printable

Printing Technology

💧 Inkjet water-based

Compatibility

Compatible with all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

Certificates



Fogra 29607-1

BENEFITS & PROPERTIES

- Reproducibility by outstanding media colour consistency
- Suitable for spot colours
- Large colour gamut
- No matting due to a high ink load
- Instant dry

KEY APPLICATIONS

Proof & Prepress

- Proofs for offset, gravure and screen printing
- Dot-proofs
- Contract, design and check proofs
- Mock-ups

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 01/2016