


# W70606 E-PHOTO® Lustre 190

## Resin-Coated Paper with Primer

### Printability

- duplex printable



### Product Specification

Property	Test Method	Dimension	Target	Tolerance
Weight	DIN EN ISO 536	g/m <sup>2</sup>	187	± 6
Thickness	DIN EN ISO 534	µm	184	± 6
	DIN EN ISO 536	mil	7.3	± 0.23
Gloss BYK	ISO 2813	60°	30	± 5
CIE Whiteness (D65/10°) min.	ISO 2469		> 140	
Opacity min.	ISO 2469	%	> 91	

### Printing Technology

- Indigo systems
- Dry Toner Systems

### Certificates

- WIR 200-years-permanence
- HP Indigo Certified Media
- HP Indigo Best Performing Substrate
- Xeikon
- FSC on request

### Key Applications

- Business cards
- Business reports
- Cookbooks
- Cover
- Greeting and invitation cards
- High quality brochures
- Menu cards
- Photos
- Photo books
- Photo Merchandise
- Photo cards

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

[felix-schoeller.com](http://felix-schoeller.com)



**FELIX SCHOELLER**

# W70606 E-PHOTO® Lustre 190

Resin-Coated Paper with Primer

## Benefits & Properties

- Excellent runnability
- Excellent toner adhesion
- Guaranteed look and feel of traditional photographic paper
- High whiteness
- No whitebreak (even without scoring)
- FSC® mix credit
- High ageing resistance (200+ years tested by Wilhelm Institute of Research)

Version: 08/2023

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

This is not a commercial specification, but a technical data sheet that describes the main characteristic of the making. Modifications reserved. In case of question, please contact the Felix Schoeller product management.

[felix-schoeller.com](https://www.felix-schoeller.com)



**FELIX SCHOELLER**